

Linear Thermal Transmittance (Ψ) and Temperature Factor (f)



Certificate No: C4TM – 001477 vs. 0 **Issued:** Thursday 30 May 2013

Issued to: Jean-Marc Bouvier
Nudura

NUDURA Corporation
International Sales & Field Support

Tel: Mob +44 (0) 7766 118711
Email: jmb@nudura.com
www.nudura.com

General Construction Specification: (see detail below for full construction)	Main/Load Bearing::	152mm (nominal) Dense Concrete Core, $\lambda \leq 2.00$
	Insulation:	2x 67mm layers of EPS + exterior extra 25mm, $\lambda = 0.036$
	Balcony:	Cast-in-situ and continuous with internal floor
	Cladding:	9mm of Render OR 102mm Brick OR other Cladding
Description:	PHPP only, ICF Wall, Balcony	
Reference:	E8	Balcony, within dwelling + 51mm extra EPS



Linear Thermal Transmittance
W/m.K

$\Psi =$ 0.675

Temperature Factor³ for Humidity and Mould

$f =$ 0.763

Calculation Prepared By: Matthew Wright MA Physics (Oxon) PGCE

Notes: Calculated for Passive House calculations only, not to be used for UK Building Regs & SAP

- Ψ and f are only valid for the detail drawn and described above.
- The Ψ and f quoted are considered valid for U-value(s) **Wall ≤ 0.185 W/m².K**, (allowance of +/- 20%, following the present guidance from B. Anderson, BRE, correspondence dated 24/02/2012, for the UK market). The use of different claddings may affect the U-value slightly, but will have no material impact on the calculated values used here, in this case.
- In dwellings, UK regulations stipulate that a temperature factor f that is >0.75 would avoid the risk of mould growth. For other nations, jurisdictions and climates, please consult the local building regulations that apply for avoiding mould and condensation. (For example, typical requirements may be: Netherlands: 0.65; Switzerland: 0.75; Belgium: 0.7; Germany: 0.7; Finland: 0.87. French, German and other standards often do not indicate a single number for acceptable risk, but are dependent on circumstances.)
- Calculations have been performed in accordance with:
 - EN ISO 10211_2007 (British Standards)
 - IP 1/06 & BR497 (BRE Press)
 and with reference to the following publications:
 EN ISO 6946 (British Standards)
 BR443 (BRE Press)